

CHEMOTEX Děčín a. s.

Děčín XXXII – Boletice nad Labem 63
407 11 Děčín
Czech Republic

Tel: +420-412-709 222**Fax: +420-412-547 200****E-mail: chemotex@chemotex.cz****www.chemotex.cz****INDAKOR D****TECHNICAL DATA SHEET****TL 162/2001**

Date of Issue: 24. 10. 2002

Date of Revision: 12. 1. 2015

Product characteristics**INDAKOR D** is boric acid amino ester.**Applications****INDAKOR D** is used as an anti-corrosion additive.**Product Features****INDAKOR D** is colourless to flavescent coloured viscous liquid.**INDAKOR D** must comply with the following quality characteristics:

Quality characteristic	Value	Methodology of assessment
Total alkalinity (mg KOH/g)	minimally 400	PN-ZM 162/2001
pH of a 1% aqueous solution	maximally 10	PN-ZM 162/2001

Directions for Use**INDAKOR D** has outstanding anti-corrosion and bacteriostatic properties, especially in case of fully synthetic products.**INDAKOR D** is used as an anti-corrosion additive for:

- Synthetic abrasive cooling fluids
- Cooling lubricant agents
- Hydraulic fluids
- Degreasing baths

The product is water soluble, miscible with surfactants and finitely miscible with mineral oils. These properties are premises for use in the mentioned applications.

Recommended dosage is from 0.5 to 2 %. The effective concentration of **INDAKOR D** must be adjusted in accordance to application conditions and experimentally verified in advance.

Packaging & Storage

INDAKOR D is delivered in 50 l PE bottles. Alternatively, it can be delivered in different containers that were discussed and agreed on in advance. Store it in a sealed container in places protected from direct climatic influences. Recommended storage temperature is between +5 to +25 °C. Storing at temperatures below 0 °C does not affect product's application properties.

Transport**INDAKOR D** is transported by covered vehicles. It is not subject to ADR/RID Regulations.**Warranty**

Provided the product is transported and stored in accordance with the above written conditions, its warranty is 6 months from the production date.

Note

Data about the product characteristics and its processing were obtained by laboratory measurements and application tests. This technical data sheet can provide solely legal advice without any engagements. Use of the product should be always adjusted to specific conditions.