

CHEMOTEX Děčín a.s.

Děčín XXXII – Boletice nad Labem 63
407 11 Děčín
Czech Republic

Tel: +420-412-547 461

Fax: +420-412-547 200

E-mail: chemotex@chemotex.cz
www.chemotex.cz

FILLER FAL

TECHNICAL DATA SHEET

TL 495/2009

Date of Issue: 22. 9. 2008

Date of Revision: 3. 7. 2013

Product characteristics

Mixture of mineral powders and an acidic catalyst.

Applications

The product is used as a base and joint putty for making chemically resistant linings and floors. It is workable to a temperature of +10 °C.

Product Features

Greyish or beige coloured powder material.

Directions for Use

FILLER FAL is a powder component of the putty EBOLIT FAL. It is mixed with EBOLIT FAL at 20 °C in the following weight ratio: **2.5 or 3.0 units of mass of the FILLER FAL per 1.0 units of mass of EBOLIT FAL**. Workability of the putty at 20 °C is at least 30 minutes and it solidifies after 24 hours. Areas to which the putty was applied can be chemically and mechanically loaded after 14 days. In case the workability of the putty is shorter, which can be caused by e.g. faster reaction of older resin **EBOLIT FAL**, a new putty in which a portion of the FILLER FAL is replaced by a FILLER 0 (which does not contain a hardening catalyst) should be prepared.

Chemical Resistance

The putty is **resistant** to diluted inorganic acids and lyes (such as sodium hydroxide, ammonium hydroxide), solutions of salts and most organic solvents including petrol, toluene, acetone and alcohols.

Packaging & Storage

FILLER FAL is delivered in 25 or 50 kg PE sacks or in 5 or 10 kg PE buckets with lid. Alternatively, it can be delivered in different containers that were discussed and agreed on in advance. The product needs to be stored in dry and enclosed storage areas. Recommended storage temperature is between +5 to +30 °C. Must not be stored in the sun or near heat sources.

Transport

FILLER FAL is transported by covered vehicles. It is not subject to ARD/RID Regulations.

Warranty

Provided the product is transported and stored in accordance with the above written conditions, its warranty is 6 months from the production date.

Note

Data about the product characteristics and its processing were obtained by laboratory measurements and application tests. This technical data sheet can provide solely legal advice without any engagements. Use of the product should be always adjusted to specific conditions.